## **Product Specification**



OSKUtex GmbH, Osterheide 3, 49124 Georgsmarienhütte, Deutschland

The Scobie and Junor (Estd. 1919) Ltd. Kelvin Industrial Estate 1 Singer Road EAST KILBRIDE G75 0XS



Manufacturer: OSKUtex GmbH, Osterheide 3, DE49124Georgsmarienhütte, GERMANY	
Article number	750-012-61
Customer article number	DAMLS110B4050
EAN-Code	4024481182242
Article type	MULTIBAR-LS schwarz (07)
	Kal. 73/50, Fb.110/40 my
	Clip und Schlaufe
Flat-width tolerance	Flat width 25 to 50 → +/- 2mm
of not converted raw extruded reel goods	Flat width 55 to 200 $\rightarrow$ +/- 3mm
	Flat width 205mm and above → +/- 4mm
Thickness tolerance	+/- 5μm
Crossways shrinkage range	All types (without RS and PR) = 8 to 12 %
	RS type = 4 to 6 %
	PR type = 6 to 10 %
The tolerances of the flat width is always refered to the fresh extruded products. In oriented multi-layer casings due to the cold/auto shrinking the flath width cannot be measurement after storage and at further processed/converted goods (shirring, setting, printing, etc.). When checking the delivered product, the remaining shrinkage has to be measured to re-calculate the initial flat width from extrusion.	
Article description	Artificial sausage casing made of polymers,
	polylayer, coextrusion, biaxial oriented
Raw good description	PA / PE
Packaging	carton box
Content per unit	1.000 ST

Article description	Artificial sausage casing made of polymers,
	polylayer, coextrusion, biaxial oriented
Raw good description	PA / PE
Packaging	carton box
Content per unit	1.000 ST
Application information	Pre-soaking for a minimum of 30 minutes
	in cold water (~15°C). In cases of pre-moistured,
	ready-to-fill products direct stuffing applicable.
Application field	Products of boiled sausages
Water permeability	< 8 g/m <sup>2</sup> d (to be expected values, measured at
(DIN 53122, 23°C, 85% rel. humidity)	45μm)
Oxygen permeability	< 20 cm <sup>3</sup> /m <sup>2</sup> d bar (to be expected values, measured
(DIN 53380, 23°C, 53% rel. humidity)	at 45µm)
Comments	
Declaration	EAN 128 with lot number / unit
Storage conditions	Store products in original closed carton boxes at 3°C
	to 24°C and 45 to 75% rel. humidity
Shelf life	24 months
counted from production date of OSKUtex	
Country of origin	Germany

The products of our artificial casings are not edible sausage casings (according to the Regulation 1169/2011/EU, Annex VI, Part C, specific requirements concerning the designation of sausage casings).

To assure traceability information on the label are required. This information is strictly confidential and not to be shared with competitors or any third parties, under any circumstances. Any infringement will entail claims for indemnification and summary dismissals where applicable. The exclusive responsibility for the use of food ingredients in different food types fells within the responsibility of the food manufacturer who has to observe existing laws and regulations for his envisaged purpose. Valid until further notice.

i.A. Pia Berlinger, Customer Service Export / KNVS, OSKUtex GmbH

Location / Date: Georgsmarienhütte, 12.11.2019

This document was electronically created by the OSKUtex GmbH and does not require any signature.

31.05.2019