



Item Code: CA21004

Description: SHRINKABLE COOKING BAG 300 X 70, 25 PER BUNDLE

PET Polyester Roastable Clipped cooking Bags

	Unit	Value	
Thickness:	Micron (q)	16-20	
Material:	Polyester		
Oxygen Permeability (cc/m <sup>2</sup> /day) Before Shrinkage	<u>Oxtran</u> 23°C, 60/70% RH	125	
After Shrinkage		60-75	
Water vapour transmission rate (g/m <sup>2</sup> /day)	<u>Lyssy</u> 38°C, 90% RH	40	
Tensile Strength (MPa)	ASTM D 882	M	200
		T	280
Modules (MPa)	ASTM D 882	M	8300
		T	4100
Elongation (%)	ASTM D 882	M	180
		T	100
Shrinkage 1min in 100°C water (%)	ASTM D 1204	M	45
		T	45
Haze	ASTM D 1003	11.5	

*PET Cooking Bags can be used to contain food during oven cooking or oven baking at temperatures above 121oC (250oF) and are compliant with European Union food contact legislation Directive 2002/72/EC (which is consolidated Directive 90/128/EEC and amendments). Disposal of this material does not present special disposal problems. In most circumstances incineration with Energy Recovery is the most environmentally efficient recovery route. It can also be burned in an incinerator with normal refuse or can be buried as a relatively inert material in a landfill. The disposal method should comply with appropriate local and country regulations.*

While we have taken all reasonable steps to verify the accuracy of the information contained in this specification, no warranties are given to this effect and purchasers should determine for themselves whether products are suitable for their own specific use. The information contained in this specification is intended for the customer it has been issued to. It must not be reproduced, or the information contained therein passed on to any third party without the written consent of Scobie & Junor.